

Heavy Conveyor Belts

UM155-G



Main industry segments



Airport, Car assembly, Cardboard converting, Cardboard manufacturing, Distribution centers, Electronics, Glass, Metal sheets and components, Plastics, Tire, Wood panel and boards, Wood surfacing

Applications

Bridge elevator belt, Cutter belt, Light package handling, Magnetic conveyor belt, Powerturn belt, Stamping belt

Special features

Abrasion resistant on both sides, Adhesive-free joint, Chemical resistant, Cut resistant, Edges wear resistant, Flexibility in all directions, Good lace retention, Impact resistant, Low friction conveying side, Low friction running side, Low noise applications suitable, No delamination, Non-marking, Oil resistant, Reverse bending, Solvent resistant, Special oil resistance for metal working, High lateral stability



Product Construction / Design	
Conveying side material	Polyester (PET) fleece
Conveying side surface	Impregnated fleece
Conveying side property	Non-adhesive
Conveying side color	Light green
Traction layer (material)	Polyester (PET) scrim
Number of Fabrics	1
Pulley side material	Polyester (PET) fleece
Pulley side surface	Impregnated fleece
Pulley side property	Non-adhesive
Pulley side color	Light green

Product characteristics	
Antistatically equipped	No
Adhesive free joining method	Ja
Flammability	No specific flammability prevention property
Food suitability, FDA conformance	No
Food suitability, EU conformance	No

Heavy Conveyor Belts

UM155-G



Technical data		
Thickness of belt	3.8 mm	0.150 tommers
Mass of belt (belt weight)	2.1 kg/m ²	0.430 lb/sqft
Tensile force for 1% elongation (k1% static) per unit of width (Habasit standard SOP3-155)	24 N/mm	135 lbf/in
Tensile force for 1% elongation after relaxation (k1% relaxed) per unit of width (Habasit Standard SOP3-155 / EN ISO 21181)	8.6 N/mm	49 lbf/in
Min. operating temperature admissible (continuous)	-12 °C	10 °F
Max. operating temperature admissible (continuous)	80 °C	176 °F
Coefficient of friction (pulley side / steel driving pulley)	0.20 -	
Coefficient of friction (pulley side / driving pulley with friction cover)	0.35 -	
Coefficient of friction (pulley side / pickled steel slider bed)	0.40 -	
Coefficient of friction (pulley side / phenolic resin slider bed)	0.30 -	
Coefficient of friction (pulley side / stainless steel slider bed)	0.25 -	
Seamless manufacturing width	2007 mm	79.00 tommers

Joining related properties

Joining method	
Hidden Flex 20 x 80	Master joining method for standard applications
Thermofix	Optional joining method
Clipper #2 SP	Optional joining method

[Link to JDS:](#)

Joining method		Hidden Flex 20 x 80	Thermofix	Clipper #2 SP
Pulley diameter (minimum)	mm <i>tommers</i>	51 <i>2.00</i>	51 <i>2.00</i>	51 <i>2.00</i>
Pulley diameter minimum with counter flection	mm <i>tommers</i>	51 <i>2.00</i>	51 <i>2.00</i>	-1 <i>2.00</i>
Admissible tensile force per unit of width	N/mm <i>lbf/in</i>	11 <i>64</i>		
Admissible tensile force per unit of width at max. operating temperature	N/mm <i>lbf/in</i>	9.3 <i>53</i>		
Slider bed suitable		Yes	Yes	Yes
Carrying rollers suitable		Yes	Yes	Yes
Troughed installation suitable		No	No	No
Powerturns / curved installations		Yes	Yes	Yes
Knife-edge (nosebar) suitable		No	No	No
Low noise applications		Yes	Yes	Yes
Metal detector suitable		No	No	No

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.

Heavy Conveyor Belts UM155-G



Chemical resistance

Link til informasjon om kemisk resistens <https://rims.habasit.com>

Mode of use or conveyance

Carrying roller, Curved, Horizontal, Slider bed

Calculations

For most applications calculation is not required. Should you still need a calculation: please ask Habasit.

Recommendation

Do not go below initial elongation (epsilon) ~ 0.3%

Check Link for Storage requirements:

["https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf"](https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf)

Exposure to water may cause a foaming on the surface of the belt. This does not affect the physical properties of the belt but could result in a residue left on the conveyed articles. This residue is easily cleaned by use of a damp cloth

Group	Nonwoven Belts
Sub-Group	Rubber Saturated Ulti-Mate Belts
Del nummer	H250000520

Ansvarsfraskrivelse

Ansvarsfraskrivelse for produktanvendelse (gælder for ALLE Habasit produkter og nævnt på alle produktdatablade)

Denne ansvarsfraskrivelse gælder for Habasit og firmaer, som er tilknyttet os, samt vores chefer, ansatte, agenter og entreprenører (herefter fælles benævnt HABASIT) for de produkter som omfattes af denne tekst (herefter benævnt produkter). SIKKERHEDSADVARSLER SKAL LÆSES OMHYGGELIGT OG ALLE ANBEFALEDE SIKKERHEDSFORSKRIFTER SKAL FØLGES STRENGT! Følg advarslerne som findes i dette dokument, i Habasits kataloger og i installationsanvisninger og håndbøger. Alle indikationer og al information om applicering, anvendelse og ydelse af produktet er anbefalinger, som kan anses for værende pålidelige, men de er ingen fremstilling, garanti eller ansvarsforpligtigelse med hensyn til fuldstændighed, tolerancer eller egnethed til et bestemt formål. Denne information bygger på laboratoriearbejde med mindre testudstyr, kørt ved normaldrift, hvilket indebærer at den ikke nødvendigvis matcher produktydelsen ved industriel anvendelse. Ny viden og erfaring kan medføre modificeringer og ændringer inden for en kort periode og uden forudgående varsel.

DISSE PRODUKTER OMFATTES AF HABASITS UDTRYKTE GARANTI, SOM ER DEN ENESTE GÆLDENDE GARANTI OG ERSTATTER ALLE ANDRE EVENTUELLE GARANTIER, UDTRYKTE ELLER UNDERFORSTÅEDE. HABASIT FRASKRIVER SIG ALT ANSVAR FOR ALLE ANDRE GARANTIER, UDTRYKTE ELLER UNDERFORSTÅEDE, INKLUSIVE, DOG UDEN AT BEGRÆNSES DERTIL, UNDERFORSTÅEDE GARANTIER OM SALGBARHED, EGNETHED TIL ET BESTEMT FORMÅL, AT PRODUKTERNE IKKE STRIDER MOD NOGLE REGLER, SAMT GARANTIER SOM FØLGE AF AFTALE, ANVENDELSE ELLER HANDEL. DETTE FORBEHOLD GÆLDER I DEN UDSTRÆKNING SOM LOVEN TILLADER. DA FORUDSÆTNINGERNE FOR ANVENDELSE ER UDEN FOR HABASITS KONTROL, KAN VI IKKE TAGE NOGET ANSVAR FOR DE NÆVNTE PRODUKTERS EGNETHED ELLER PROCES TILPASNING. DETTE FORBEHOLD GÆLDER OGSÅ FOR INDIKATIONER FRA PROCESRESULTATER OG OUTPUT.