

Power Transmission Belts

SR-14/15



Main industry segments



Agriculture, Cardboard converting, Hygiene products, Paper printing and finishing, Yarn processing

Applications

Driving belt, Tangential belt

Special features

Abrasion resistant, Constant coefficient of friction, Forgiving in case of short term shock like overloads, Robustness



Product Construction / Design

Pulley side material	Acrylonitrile-Butadiene-Rubber (NBR) as friction cover (pulley/cylinder side)
Pulley side surface	Rough structure
Pulley side color	Black
Traction layer (material)	Polyamide (PA)
Number of Fabrics	2
Opposite side material	Acrylonitrile-Butadiene-Rubber (NBR) as friction cover (whirl side)
Opposite side surface	Rough structure
Opposite side color	Black

Product characteristics

Drive determination	Double-sided power transmission
Antistatically equipped	Yes
Adhesive free joining method	Nei
Food suitability, FDA conformance	No
Food suitability, EU conformance	No

Technical data

Thickness of belt	1.5 mm	0.059	tommer
Mass of belt (belt weight)	1.5 kg/m ²	0.307	lb/sqft
Tensile force for 1% elongation (k1% after running in) per unit of width (Habasit standard SOP3-013)	4.4 N/mm	25	lbf/in
Nominal peripheral force per unit of width	12 N/mm	69	lbf/in
Min. operating temperature admissible (continuous)	-20 °C	-4	°F
Max. operating temperature admissible (continuous)	100 °C	212	°F
Seamless manufacturing width	1140 mm	44.88	tommer

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554).

Power Transmission Belts

SR-14/15



Joining related properties

[Link to JDS:](#)

Joining method		Thermofix 75°
Pulley diameter (minimum)	mm <i>tommer</i>	40 1.57
Pulley diameter minimum with counter flection	mm <i>tommer</i>	40 1.57

Chemical resistance

Link til informasjon om kemisk resistens <https://rims.habasit.com>

Mode of use or conveyance

Power transmission

Calculations

With power transmission belts a calculation at least of the belt width and initial elongation is highly recommended. For this serves the Habasit SeleCalc calculation program. The easiest way is to have belt drives calculated by Habasit representatives.

Recommendation

Do not go below initial elongation (epsilon) ~ 0.5%

Store spare belts in a cool and dry place and if possible in their original packaging. Protect spare belts from sunlight/UV-radiation/dust/dirt! Check Link for Storage requirements:

["https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf"](https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf)

This product has not been tested according to ATEX standards (atmospheres with explosion risk - ATEX 95 regulation or EU directive 2014/34/EU) and therefore is subject to user's analysis in the respective environment

Group	Polyamide Power Transmission Belts
	SP Polyamide Power Transmission Belts
Del nummer	H950044637

Ansvarsfraskrivelse

Ansvarsfraskrivelse for produktanvendelse (gælder for ALLE Habasit produkter og nævnt på alle produktdatablade)

Denne ansvarsfraskrivelse gælder for Habasit og firmaer, som er tilknyttet os, samt vores chefer, ansatte, agenter og entreprenører (herefter fælles benævnt HABASIT) for de produkter som omfattes af denne tekst (herefter benævnt produkter). SIKKERHEDSADVARSLER SKAL LÆSES OMHYGGELIGT OG ALLE ANBEFALEDE SIKKERHEDSFORSKRIFTER SKAL FØLGES STRENGT! Følg advarslerne som findes i dette dokument, i Habasits kataloger og i installationsanvisninger og håndbøger. Alle indikationer og al information om applicering, anvendelse og ydelse af produktet er anbefalinger, som kan anses for værende pålidelige, men de er ingen fremstilling, garanti eller ansvarsforpligtigelse med hensyn til fuldstændighed, tolerancer eller egnethed til et bestemt formål. Denne information bygger på laboratoriearbejde med mindre testudstyr, kørt ved normaldrift, hvilket indebærer at den ikke nødvendigvis matcher produktydelsen ved industriel anvendelse. Ny viden og erfaring kan medføre modificeringer og ændringer inden for en kort periode og uden forudgående varsel. DISSE PRODUKTER OMFATTES AF HABASITS UDTRYKTE GARANTI, SOM ER DEN ENESTE GÆLDENDE GARANTI OG ERSTATTER ALLE ANDRE EVENTUELLE GARANTIER, UDTRYKTE ELLER UNDERFORSTÅEDE. HABASIT FRASKRIVER SIG ALT ANSVAR FOR ALLE ANDRE GARANTIER, UDTRYKTE ELLER UNDERFORSTÅEDE, INKLUSIVE, DOG UDEN AT BEGRÆNSES DERTIL, UNDERFORSTÅEDE GARANTIER OM SALGBARHED, EGNETHED TIL ET BESTEMT FORMÅL, AT PRODUKTERNE IKKE STRIDER MOD NOGLE REGLER, SAMT GARANTIER SOM FØLGE AF AFTALE, ANVENDELSE ELLER HANDEL. DETTE FORBEHOLD GÆLDER I DEN UDSTRÆKNING SOM LOVEN TILLADER. DA FORUDSÆTNINGERNE FOR ANVENDELSE ER UDEN FOR HABASITS KONTROL, KAN VJ IKKE TAGE NOGET ANSVAR FOR DE NÆVNTE PRODUKTERS EGNETHED ELLER PROCESTILPASNING. DETTE FORBEHOLD GÆLDER OGSÅ FOR INDIKATIONER FRA PROCESRESULTATER OG OUTPUT.