

### Applications

Thermofix joining

### Scope of application

Habasit products containing a rubber layer



### DANGER

H225	Highly flammable liquid and vapour
H319	Causes serious eye irritation
H336	May cause drowsiness or dizziness

### Product characteristics

Description and appearance of the mixture	
Item number	H010701726
UFI	YF00-Q070-F00M-44NU
Designated material	Adhesive for rubber
Use	Liquid
Color	Bright yellow
Odor	Like acetone
Viscosity	Approx. 2 Pas
Composition	TPU resin in acetone
Size of trading unit	35 g in aluminium can
SDS	<a href="https://www.safin-net.com/de/MobileView.aspx?ck=1238991301&amp;type=SDB&amp;name=aa954f32-d2f0-41b3-86c0-2dec02827c61&amp;file=sdb.doc&amp;user=MobileUser">https://www.safin-net.com/de/MobileView.aspx?ck=1238991301&amp;type=SDB&amp;name=aa954f32-d2f0-41b3-86c0-2dec02827c61&amp;file=sdb.doc&amp;user=MobileUser</a>



Shelf life, storage and disposal	
Shelf life	Printed on container
Storage	Keep containers tightly closed in a dry, cool and well-ventilated place. Do not store together with food.
Disposal	Dispose of as hazardous waste in compliance with local and national regulations. Can be burned in a suitable installation subject to local regulations.

Handling and application	
Application tools and auxiliaries	Brush, spatula
Parameter for joining	Detailed information about temperature, pressure and duration of joining can be found in the Joining Data Sheet (JDS)
Standard climatic conditions	23°C (73° F); 50 % rel. humidity

### Processing specification

Use only with personal protective equipment (safety glasses, gloves, in case of insufficient ventilation wear suitable respiratory equipment).

Mark off area for gluing. This area must be clean from dirt and impurity. Mix Rubcol A and Rubcol B completely. The mixture starts hardening after 3 hours. Apply the adhesive with a brush and rub in with brush on both areas. Allow to dry for 30 min. Put glued surfaces accurately on top of each other at the first attempt.

The use of a Habasit hot-pressing device is recommended. Pressing time is individual for each belt and can be checked up in the JDS. Attention should be paid to the climatic conditions. Deviation from standard climatic conditions may need an adjustment for pressing time and temperature.

For industrial purpose only and for use according to our technical regulations only.

### Disclaimer

#### Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice.

EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.