

# Monolithic Flat Belts

## CD.F12-N-HC+EH/EH-EP



### Main industry segments



Biscuit and Crackers, Chocolate, Convenience food, Frozen food, Poultry, Primary food packaging, Ready meals, Red meat

### Applications

Diverting belt, Packaging belt, Weighing belt

### Special features

Abrasion resistant, Edges wear resistant, Elastic, Flexibility in all directions, Hydrolysis resistant, Monolithic Belt, Oil and fat resistant, Small pulley diameter suitable, Suitable for UV-C disinfection, UV resistant



Product Construction / Design	
Material	Thermoplastic polyurethane (TPU)
Color	Cobalt blue / Black
Conveying side surface	Medium textile structure
Conveying side property	Medium-adhesive
Conveying side color	Cobalt blue
Pulley side surface	Medium textile structure
Pulley side property	Medium-adhesive
Pulley side color	Black

Product characteristics	
Antistatically equipped	Yes - fulfills EN 12882 / Categorie 1
Knife edge roller suitable	Yes
Antimicrobially equipped	No
Conveying side conductive surface acc. EN ISO	No
Slider bed suitable	Yes
Carrying rollers suitable	Yes
Troughed installation suitable	Yes
UV-C suitable	Yes
Flammability	No specific flammability prevention property
Food suitability, EU conformance	Yes - Check Document of Compliance (DoC) in our Portal
Food suitability, FDA conformance	Yes - Check Document of Compliance (DoC) in our Portal
Food suitability, USDA recommendations	No use intended

# Monolithic Flat Belts

## CD.F12-N-HC+EH/EH-EP



Technical data				
Hardness	89	Shore A		
Thickness of belt	1.20	mm	0.05	inch
Mass of belt (belt weight)	1.1	kg/m <sup>2</sup>	0.225	lb/sqft
Tensile force for 1% elongation (k1% static) per unit of width (Habasit standard SOP3-155)	0.25	N/mm	1	lbf/in
Tensile force for 1% elongation after relaxation (k1% relaxed) per unit of width (Habasit Standard SOP3-155 / EN ISO 21181)	0.20	N/mm	1	lbf/in
Min. operating temperature admissible (continuous)	-20	°C	-4	°F
Max. operating temperature admissible (continuous)	60	°C	140	°F
Coefficient of friction (pulley side / steel driving pulley)	0.40	-		
Coefficient of friction (pulley side / stainless steel slider bed)	0.30	-		
Coefficient of friction (PE sliding support)	0.35	-		
Seamless manufacturing width	1350	mm	53.15	inch

### Joining related properties

Joining method	
Quickmelt	Master joining method for standard applications
Microflex 15 x 10	Optional joining method
Flexproof 8 x 30	Optional joining method

[Link to JDS:](#)

Joining method		Quickmelt	Microflex 15 x 10	Flexproof 8 x 30
Knife edge roller diameter (minimum)	mm inch	8 0.315	8 0.315	8 0.315
Pulley diameter (minimum)	mm inch	12 0.47	12 0.47	12 0.47
Pulley diameter minimum with counter flection	mm inch	12 0.47	12 0.47	12 0.47
Admissible tensile force per unit of width	N/mm lbf/in	1.0 6	1.0 6	1.0 6
Admissible tensile force per unit of width at max. operating temperature	N/mm lbf/in	0.20 1	0.20 1	0.20 1

*All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.*

### Chemical resistance

Link to 'Chemical resistance information': <https://rims.habasit.com>

### Calculations

For most applications calculation is not required. Should you still need a calculation: please ask Habasit.

# Monolithic Flat Belts

## CD.F12-N-HC+EH/EH-EP



### Recommendation

Do not go below initial elongation (epsilon) ~ 1.0%, Elastic belt: Initial elongation depends on belt load and application

Store spare belts in a cool and dry place and if possible in their original packaging. Protect spare belts from sunlight/UV-radiation/dust/dirt! Check Link for Storage requirements:

["https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf"](https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf)

This product has not been tested according to ATEX standards (atmospheres with explosion risk - ATEX 95 regulation or EU directive 2014/34/EU) and therefore is subject to user's analysis in the respective environment

Group	Cleandrive Friction Drive
Sub-Group	Monolithic Flat Belts
Item number	H700016168

### Disclaimer

#### Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice.

EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.