

PQ-02 Round belts joining kit

The PQ-02 is a simple and cost effective tool for welding of Polycord round belts. The joining operation is by blunt welding: ends of the belt are melted by pressing them against the surface of a precisely regulated hot welding plate. After sufficient heating belt ends are pressed against each other with a defined pressure and left to cool in a defined position. After removing the resulting bead with a knife or by grinding an optimum quality round belt is ready for use. The PQ-02 is well suitable for on-site installation and small to medium size series fabrication in the workshop.



| | | |
|------------------------|-----------------------|-----------|
| Adjustable Temperature | Adjustable by trimmer | |
| Cooling Media | Ambient air | |
| Max Belt Thickness | 15 mm | 0.59 inch |
| Belt/tape width max. | 15 mm | 0.6 inch |
| Custom Tariff | 85158090 | |

| Available versions | Item number | Power supply |
|--------------------|-------------|---------------|
| PQ-02/6 | H088000540 | 1ph 120V 60Hz |
| PQ-02/8 | H088000541 | 1ph 230V 50Hz |

| Available versions | Length | Width | Height | Weight |
|--------------------|------------------------|-------------------------|-------------------------|---------------------|
| PQ-02/6 | 420 mm (16.535 inch) | 140.0 mm (5.512 inch) | 120.0 mm (4.724 inch) | 0.300 kg (0.7 lb) |
| PQ-02/8 | 420 mm (16.535 inch) | 140.0 mm (5.512 inch) | 120.0 mm (4.724 inch) | 0.300 kg (0.7 lb) |

Disclaimer

Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice. EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.