

Elastic round belts

E-RB-H




Main application

Live roller drive belt, Power transmission belt

Description

Elastic, Oil resistant, Monolithic Belt, Abrasion resistant, Flexibility in all directions



Product data

Technical data	
Material type	TPU Polyether
Hardness	87 ShA
Temperature correction factor	0.85
Min. operating temperature admissible (continuous)	-20 °C
Max. operating temperature admissible (continuous)	50 °C
Coefficient of friction on steel	0.40

Code	Item number	Color	Food grade	DoC Name	Ø	Package	Quantity	Units	Weight
					mm				
					kg				
E-RB03-HC-C300	H090031186	Cobalt blue	Yes	HC	3	Coil	300	M	0.008
E-RB04-HC-C250	H090031187	Cobalt blue	Yes	HC	4	Coil	250	M	0.014
E-RB05-HC-C250	H090031185	Cobalt blue	Yes	HC	5	Coil	250	M	0.022
E-RB06-HC-C250	H090031188	Cobalt blue	Yes	HC	6	Coil	250	M	0.032
E-RB08-HC-C200	H090031189	Cobalt blue	Yes	HC	8	Coil	200	M	0.056
E-RB10-HC-C100	H090031190	Cobalt blue	Yes	HC	10	Coil	100	M	0.088
E-RB12-HC-C100	H090031191	Cobalt blue	Yes	HC	12	Coil	100	M	0.127

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.

Code	Tensile force for 8% elongation (k8% static) (Habasit Standard SOP3-155 / EN ISO 21181):	Tensile force for 8% elongation after relaxation (k8% relaxed) (Habasit Standard SOP3-155 / EN ISO 21181):	Nominal peripheral force	Pulley diameter (minimum)	Minimum pulley diameter running side
		N	N	mm	mm
E-RB03-HC-C300	13	9	15	30	30
E-RB04-HC-C250	23	15	27	40	40
E-RB05-HC-C250	36	24	42	50	50
E-RB06-HC-C250	52	34	61	60	60
E-RB08-HC-C200	92	61	108	80	80
E-RB10-HC-C100	143	95	169	100	100
E-RB12-HC-C100	206	136	244	120	120

Chemical resistance

Link to 'Chemical resistance information': <https://rims.habasit.com>

Recommendation

General dimensional tolerance: $\pm 3\%$ or ± 0.20 mm (whichever is greater).

Disclaimer

Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice. EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.