


### Main application

Live roller drive belt, Power transmission belt

### Description

Elastic, Monolithic Belt, High grip surface, Abrasion resistant, Flexibility in all directions, Simple and fast joining method



### Product data

Technical data	
Material type	TPU Polyester
Hardness	90 ShA
Geometry Option	Rough
Temperature correction factor	0.85
Min. operating temperature admissible (continuous)	-20 °C
Max. operating temperature admissible (continuous)	50 °C
Coefficient of friction on steel	0.40

Code	Item number	Color	Food grade	Ø	Package	Quantity	Units	Weight
				mm				kg
E-RB03-KG-C300+R	H090031359	Green	No	3	Coil	300	M	0.008
E-RB04-KG-C250+R	H090031358	Green	No	4	Coil	250	M	0.015
E-RB05-KG-C250+R	H090031360	Green	No	5	Coil	250	M	0.023
E-RB06-KG-C250+R	H090031361	Green	No	6	Coil	250	M	0.033
E-RB08-KG-C200+R	H090031363	Green	No	8	Coil	200	M	0.059
E-RB12-KG-C100+R	S090031365	Green	No	12	Coil	100	M	0.133
E-RB15-KG-C50+R	H090031366	Green	No	15	Coil	50	M	0.209

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.

Code	Tensile force for 8% elongation (k8% static) (Habasit Standard SOP3-155 / EN ISO 21181):	Tensile force for 8% elongation after relaxation (k8% relaxed) (Habasit Standard SOP3-155 / EN ISO 21181):	Nominal peripheral force	Pulley diameter (minimum)	Minimum pulley diameter running side
	N	N	N	mm	mm
E-RB03-KG-C300+R	18	13	23	30	30
E-RB04-KG-C250+R	32	24	41	40	40
E-RB05-KG-C250+R	51	37	65	50	50
E-RB06-KG-C250+R	73	53	93	60	60
E-RB08-KG-C200+R	129	94	165	80	80
E-RB12-KG-C100+R	291	212	372	120	120
E-RB15-KG-C50+R	455	331	582	150	150

### Chemical resistance

Link to 'Chemical resistance information': <https://rims.habasit.com>

### Recommendation

General dimensional tolerance:  $\pm 3\%$  or  $\pm 0.20$  mm (whichever is greater).

Given one section of product, the rough finishing coverage will be  $>75\%$

### Disclaimer

#### Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice. EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.