

HabasisLINK® Material Data Sheet

Wear resistant Polyoxymethylene (Acetal)

POM+PK



Material description

- Developed for demanding applications in the automotive industry
- Very high wear and abrasion resistance
- High fatigue resistance
- Low coefficient of friction

コード	Material	Property	Density	Temperature range	Habasis colors
			g/cm ³		
POM+PK	Wear resistant Polyoxymethylene	Extra wear resistant thermoplastic material with high strength, low coefficient of friction and very good fatigue resistance. Good chemical resistance to oil and alkalines, but not suitable for long-term contact with high concentration of acids.	1.42	Wet conditions: -40°C to +60°C -40°F to +140°F Dry conditions: -40°C to +93°C -40°F to +200°F	black dark-grey

Thermal expansion	mm/m*°C	in/ft**F
Coeff. of linear thermal expansion α	0.09	0.0006

Sprocket material

Application	Rod material	Sprocket material
dry, abrasive, medium load	PA	PA or TPU
dry, abrasive, high load	PA or Steel	PA or Steel
wet, abrasive, medium load	PA ¹⁾	PA or TPU
wet, abrasive, high load	PA ¹⁾ or Steel	PA or Steel

1) Dimension change needs to be considered

Habasis support for design and calculation

To assist the layout and calculation of Habasis plastic modular belt conveyors, Habasis provides additional documentation and instruments on request.

- Engineering Guide with further complementary details to the design and calculation of conveyors.
- Calculation Program to analyze the dimensioning and acting forces of a planned conveyor design.

For further information or additional documentation please contact Habasis.

HabasitLINK® Material Data Sheet

Wear resistant Polyoxymethylene (Acetal)

POM+PK



Disclaimer

Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice.

EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.