

HabiPLAST™ Material Data Sheet

Habital POM for machined parts



Material description

- Polyacetal copolymer
- Good sliding and wear properties
- Good resistance to fuels, oil and grease

コード	Property
POMC-B	

Material properties

General	Nominal value
Code	POMC-B
Color	black
Density	1.41 g/cm ³
Water absorbtion 42h / 96h (23°C)	0.24% / 0.45%
Water absorbtion at 23°C, 50% rel H	0.2%
Water absorbtion at 23°C, in water	0.8%
Thermal	Nominal value
Temperature range	Dry: -50°C to +100°C Wet: -50°C to +60°C
Coeff. of linear thermal expansion a	0.12 mm/(m•K)
Thermal conductivity	0.31 W/(m•K)
Electrical	Nominal value
Volume resistivity	10 ¹⁴ Ohm•cm
Surface resistivity	10 ¹³ Ohm
Mechanical	Nominal value
Tensile modulus	2800 MPa
Tensile strength (ultimate)	66 Mpa
Tensile elongation (break)	50%
Ball indentation hardness	140 MPa

Coefficient of friction

Product	Friction (-)
HabasitLINK PE	0.23

Habasit support for design and calculation

To assist the layout and calculation of Habasit plastic modular belt conveyors, Habasit provides additional documentation and instruments on request.

- Engineering Guide with further complementary details to the design and calculation of conveyors.
- Calculation Program to analyze the dimensioning and acting forces of a planned conveyor design.

For further information or additional documentation please contact Habasit.



Disclaimer

Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice.

EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.