

Food Belts

NAB-20EFWV-A2F1



Main industry segments


Sugar

Applications

Food processing/conveying belt, Transfer belt

Special features

Reverse side coated, ATEX compliant



Product Construction / Design	
Conveying side material	Polyvinylchloride (PVC)
Conveying side surface	Matt
Conveying side property	Adhesive
Conveying side color	White
Traction layer (material)	Polyester (PET)
Number of Fabrics	3
Pulley side material	Polyvinylchloride (PVC)
Pulley side surface	Matt
Pulley side property	Adhesive
Pulley side color	White

Product characteristics	
Antistatically equipped	Yes
Adhesive free joining method	Ja
Flammability	In accordance with ISO 340
Food suitability, FDA conformance	Yes - Check Document of Compliance (DoC) in our Portal
Food suitability, EU conformance	Yes - Check Document of Compliance (DoC) in our Portal

Technical data			
Thickness of belt	5.5	mm	0.22 <i>tommer</i>
Mass of belt (belt weight)	6.9	kg/m ²	1.413 <i>lb/sqft</i>
Tensile force for 1% elongation (k1% static) per unit of width (Habasit standard SOP3-155)	19	N/mm	108 <i>lbf/in</i>
Tensile force for 1% elongation after relaxation (k1% relaxed) per unit of width (Habasit Standard SOP3-155 / EN ISO 21181)	10	N/mm	57 <i>lbf/in</i>
Min. operating temperature admissible (continuous)	-10	°C	14 °F
Max. operating temperature admissible (continuous)	80	°C	176 °F
Coefficient of friction (pulley side / steel driving pulley)	0.35	-	
Coefficient of friction (pulley side / driving pulley with friction cover)	0.40	-	
Coefficient of friction (pulley side / pickled steel slider bed)	0.60	-	
Coefficient of friction (pulley side / phenolic resin slider bed)	0.60	-	
Coefficient of friction (pulley side / stainless steel slider bed)	0.60	-	
Seamless manufacturing width	2850	mm	112.20 <i>tommer</i>

Joining related properties

Joining method		
Flexproof 10 x 80	Master joining method for standard applications	

[Link to JDS:](#)

Joining method		Flexproof 10 x 80
Pulley diameter (minimum)	mm <i>tommer</i>	200 7.87
Pulley diameter minimum with counter flection	mm <i>tommer</i>	250 9.84
Admissible tensile force per unit of width	N/mm <i>lbf/in</i>	25 143
Admissible tensile force per unit of width at max. operating temperature	N/mm <i>lbf/in</i>	11 63
Slider bed suitable		No
Carrying rollers suitable		Yes
Troughed installation suitable		Yes
Powerturns / curved installations		No
Knife-edge (nosebar) suitable		No
Low noise applications		No
Metal detector suitable		No

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.

Chemical resistance

Link til informasjon om kemisk resistens <https://rims.habasit.com>

Mode of use or conveyance

Horizontal, Inclined

Calculations

For most applications calculation is not required. Should you still need a calculation: please ask Habasit.

Recommendation

Do not go below initial elongation (epsilon) ~ 0.3%

Store spare belts in a cool and dry place and if possible in their original packaging. Protect spare belts from sunlight/UV-radiation/dust/dirt! Check Link for Storage requirements:

["https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf"](https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf)

Group	PVC Belts
Sub-Group	General Purpose Belts
Del nummer	H100066308

Ansvarsfraskrivelse

Ansvarsfraskrivelse for produktanvendelse (gælder for ALLE Habasit produkter og nævnt på alle produktdatablade)

Denne ansvarsfraskrivelse gælder for Habasit og firmaer, som er tilknyttet os, samt vores chefer, ansatte, agenter og entreprenører (herefter fælles benævnt HABASIT) for de produkter som omfattes af denne tekst (herefter benævnt produkter). SIKKERHEDSADVARSLER SKAL LÆSES OMHYGGELIGT OG ALLE ANBEFALEDE SIKKERHEDSFORSKRIFTER SKAL FØLGES STRENGT! Følg advarslerne som findes i dette dokument, i Habasits kataloger og i installationsanvisninger og håndbøger. Alle indikationer og al information om applicering, anvendelse og ydelse af produktet er anbefalinger, som kan anses for værende pålidelige, men de er ingen fremstilling, garanti eller ansvarsforpligtigelse med hensyn til fuldstændighed, tolerancer eller egnethed til et bestemt formål. Denne information bygger på laboratoriearbejde med mindre testudstyr, kørt ved normaldrift, hvilket indebærer at den ikke nødvendigvis matcher produktydelsen ved industriel anvendelse. Ny viden og erfaring kan medføre modificeringer og ændringer inden for en kort periode og uden forudgående varsel.

DISSE PRODUKTER OMFATTES AF HABASITS UDTRYKTE GARANTI, SOM ER DEN ENESTE GÆLDENDE GARANTI OG ERSTATTER ALLE ANDRE EVENTUELLE GARANTIER, UDTRYKTE ELLER UNDERFORSTÅEDE. HABASIT FRASKRIVER SIG ALT ANSVAR FOR ALLE ANDRE GARANTIER, UDTRYKTE ELLER UNDERFORSTÅEDE, INKLUSIVE, DOG UDEN AT BEGRÆNSES DERTIL, UNDERFORSTÅEDE GARANTIER OM SALGBARHED, EGNETHED TIL ET BESTEMT FORMÅL, AT PRODUKTERNE IKKE STRIDER MOD NOGLE REGLER, SAMT GARANTIER SOM FØLGE AF AFTALE, ANVENDELSE ELLER HANDEL. DETTE FORBEHOLD GÆLDER I DEN UDSTRÆKNING SOM LOVEN TILLADER. DA FORUDSÆTNINGERNE FOR ANVENDELSE ER UDEN FOR HABASITS KONTROL, KAN VJ IKKE TAGE NOGET ANSVAR FOR DE NÆVNTE PRODUKTERS EGNETHED ELLER PROCESTILPASNING. DETTE FORBEHOLD GÆLDER OGSÅ FOR INDIKATIONER FRA PROCESRESULTATER OG OUTPUT.