

Processing Belts

XVT-2204



Main industry segments



Paper manufacturing and processing, Paper printing and finishing, Secondary packaging

Applications

Decline belt, Incline belt, Powerturn belt, Processing belt

Special features

Abrasion resistant, Constant coefficient of friction, High coefficient of friction surface, Ozone resistant, Powerturn suitable, UV resistant, Versatile, Robustness



| Product Construction / Design | |
|-------------------------------|-------------------------|
| Conveying side material | Rubber (EPDM) |
| Conveying side surface | Rough textile structure |
| Conveying side property | Adhesive |
| Conveying side color | Anthracite |
| Traction layer (material) | Polyester (PET) |
| Number of Fabrics | 2 |
| Pulley side material | Polyester (PET) |
| Pulley side surface | Fabric |
| Pulley side property | Non-adhesive |
| Pulley side color | Off-white |

| Product characteristics | |
|--|--|
| Antistatically equipped | No |
| Adhesive free joining method | Ja |
| Flammability | No specific flammability prevention property |
| Food suitability, FDA conformance | No |
| Food suitability, USDA recommendations | No use intended |
| Food suitability, EU conformance | No |

Processing Belts

XVT-2204



| Technical data | | |
|---|-----------------------|----------------------|
| Thickness of belt | 1.9 mm | 0.07 <i>tommer</i> |
| Mass of belt (belt weight) | 1.8 kg/m ² | 0.369 <i>lb/sqft</i> |
| Tensile force for 1% elongation (k1% static) per unit of width (Habasit standard SOP3-155) | 20 N/mm | 114 <i>lbf/in</i> |
| Tensile force for 1% elongation after relaxation (k1% relaxed) per unit of width (Habasit Standard SOP3-155 / EN ISO 21181) | 13 N/mm | 74 <i>lbf/in</i> |
| Min. operating temperature admissible (continuous) | -30 °C | -22 °F |
| Max. operating temperature admissible (continuous) | 80 °C | 176 °F |
| Coefficient of friction (pulley side / steel driving pulley) | 0.15 - | |
| Coefficient of friction (pulley side / driving pulley with friction cover) | 0.35 - | |
| Coefficient of friction (pulley side / pickled steel slider bed) | 0.20 - | |
| Seamless manufacturing width | 2400 mm | 94.49 <i>tommer</i> |

Joining related properties

| Joining method | |
|-------------------|---|
| Flexproof 10 x 80 | Master joining method for standard applications |

[Link to JDS:](#)

| Joining method | | Flexproof 10 x 80 |
|--|-----------------------|-------------------|
| Pulley diameter (minimum) | mm <i>tommer</i> | 40 1.57 |
| Pulley diameter minimum with counter flection | mm <i>tommer</i> | 50 1.97 |
| Admissible tensile force per unit of width | N/mm <i>lbf/in</i> | 19 108 |
| Admissible tensile force per unit of width at max. operating temperature | N/mm <i>lbf/in</i> | 8.0 46 |
| Slider bed suitable | | Yes |
| Carrying rollers suitable | | Yes |
| Troughed installation suitable | | Yes |
| Powerturns / curved installations | | Yes |
| Knife-edge (nosebar) suitable | | No |
| Metal detector suitable | | No |

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.

Processing Belts

XVT-2204



Chemical resistance

Link til informasjon om kemisk resistens <https://rims.habasit.com>

Mode of use or conveyance

Declined, Horizontal, Inclined

Calculations

For most applications calculation is not required. Should you still need a calculation: please ask Habasit.

Recommendation

Do not go below initial elongation (epsilon) ~ 0.3%, Install the slack belt and tension until running perfectly under the full belt load

Store spare belts in a cool and dry place and if possible in their original packaging. Protect spare belts from sunlight/UV-radiation/dust/dirt! Check Link for Storage requirements:

["https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf"](https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf)

This product has not been tested according to ATEX standards (atmospheres with explosion risk - ATEX 95 regulation or EU directive 2014/34/EU) and therefore is subject to user's analysis in the respective environment

| | |
|------------|-----------------------------------|
| Group | Elastomer Covered Conveying Belts |
| Sub-Group | - |
| Del nummer | H010101611 |

Ansvarsfraskrivelse

Ansvarsfraskrivelse for produktanvendelse (gælder for ALLE Habasit produkter og nævnt på alle produktdatablade)

Denne ansvarsfraskrivelse gælder for Habasit og firmaer, som er tilknyttet os, samt vores chefer, ansatte, agenter og entreprenører (herefter fælles benævnt HABASIT) for de produkter som omfattes af denne tekst (herefter benævnt produkter). SIKKERHEDSADVARSLER SKAL LÆSES OMHYGGELIGT OG ALLE ANBEFALEDE SIKKERHEDSFORSKRIFTER SKAL FØLGES STRENGT! Følg advarslerne som findes i dette dokument, i Habasits kataloger og i installationsanvisninger og håndbøger. Alle indikationer og al information om applicering, anvendelse og ydelse af produktet er anbefalinger, som kan anses for værende pålidelige, men de er ingen fremstilling, garanti eller ansvarsforpligtigelse med hensyn til fuldstændighed, tolerancer eller egnethed til et bestemt formål. Denne information bygger på laboratoriearbejde med mindre testudstyr, kørt ved normaldrift, hvilket indebærer at den ikke nødvendigvis matcher produkttydelsen ved industriel anvendelse. Ny viden og erfaring kan medføre modificeringer og ændringer inden for en kort periode og uden forudgående varsel.

DISSE PRODUKTER OMFATTES AF HABASITS UDTRYKTE GARANTI, SOM ER DEN ENESTE GÆLDENDE GARANTI OG ERSTATTER ALLE ANDRE EVENTUELLE GARANTIER, UDTRYKTE ELLER UNDERFORSTÅEDE. HABASIT FRASKRIVER SIG ALT ANSVAR FOR ALLE ANDRE GARANTIER, UDTRYKTE ELLER UNDERFORSTÅEDE, INKLUSIVE, DOG UDEN AT BEGRÆNSES DERTIL, UNDERFORSTÅEDE GARANTIER OM SALGBARHED, EGNETHED TIL ET BESTEMT FORMÅL, AT PRODUKTERNE IKKE STRIDER MOD NOGLE REGLER, SAMT GARANTIER SOM FØLGE AF AFTALE, ANVENDELSE ELLER HANDEL. DETTE FORBEHOLD GÆLDER I DEN UDSTRÆKNING SOM LOVEN TILLADER. DA FORUDSÆTNINGERNE FOR ANVENDELSE ER UDEN FOR HABASITS KONTROL, KAN VI IKKE TAGE NOGET ANSVAR FOR DE NÆVNTE PRODUKTERS EGNETHED ELLER PROCESILPASNING. DETTE FORBEHOLD GÆLDER OGSÅ FOR INDIKATIONER FRA PROCESRESULTATER OG OUTPUT.