

Processing Belts

SAG-12E



Main industry segments



Cardboard converting, Distribution centers

Applications

Decline belt, Incline belt, Processing belt

Special features

Constant coefficient of friction, High coefficient of friction surface, Ozone resistant, UV resistant, Robustness



Product Construction / Design	
Conveying side material	Rubber (EPDM)
Conveying side surface	Grip structure
Conveying side property	Adhesive
Conveying side color	Anthracite
Traction layer (material)	Polyester (PET)
Number of Fabrics	2
Pulley side material	Polyester (PET)
Pulley side surface	Fabric
Pulley side property	Non-adhesive
Pulley side color	Off-white

Product characteristics	
Antistatically equipped	Yes
Adhesive free joining method	No
Flammability	Tested according to UL 94HB (USA) requirement; HB= Horizontal Burning
Food suitability, FDA conformance	No
Food suitability, USDA recommendations	No use intended
Food suitability, EU conformance	No

Processing Belts

SAG-12E



Technical data		
Thickness of belt	5.2 mm	0.20 inch
Mass of belt (belt weight)	4.2 kg/m ²	0.860 lb/sqft
Tensile force for 1% elongation (k1% static) per unit of width (Habasit standard SOP3-155)	17 N/mm	97 lbf/in
Tensile force for 1% elongation after relaxation (k1% relaxed) per unit of width (Habasit Standard SOP3-155 / EN ISO 21181)	12 N/mm	69 lbf/in
Min. operating temperature admissible (continuous)	-30 °C	-22 °F
Max. operating temperature admissible (continuous)	100 °C	212 °F
Coefficient of friction (pulley side / steel driving pulley)	0.15 -	
Coefficient of friction (pulley side / driving pulley with friction cover)	0.35 -	
Coefficient of friction (pulley side / pickled steel slider bed)	0.20 -	
Coefficient of friction (pulley side / phenolic resin slider bed)	0.15 -	
Coefficient of friction (pulley side / stainless steel slider bed)	0.15 -	
Seamless manufacturing width	1200 mm	47.24 inch

Joining related properties

Joining method	
Thermofix 90°	Master joining method for standard applications

[Link to JDS:](#)

Joining method		Thermofix 90°
Pulley diameter (minimum)	mm inch	60 2.36
Pulley diameter minimum with counter flection	mm inch	80 3.15
Admissible tensile force per unit of width	N/mm lbf/in	30 171
Admissible tensile force per unit of width at max. operating temperature	N/mm lbf/in	19 108
Slider bed suitable		Yes
Carrying rollers suitable		Yes
Troughed installation suitable		No
Powerturns / curved installations		No
Knife-edge (nosebar) suitable		No
Low noise applications		No
Metal detector suitable		No

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.

Processing Belts

SAG-12E



Chemical resistance

Link to 'Chemical resistance information': <https://rims.habasit.com>

Mode of use or conveyance

Declined, Horizontal, Inclined

Calculations

For most applications calculation is not required. Should you still need a calculation: please ask Habasit.

Recommendation

Do not go below initial elongation (epsilon) ~ 0.3%, Install the slack belt and tension until running perfectly under the full belt load

Protect belts from sunlight/UV-radiation/dust and dirt. Store spare belts in a cool and dry place and if possible in their original packaging. Check Link for Storage requirements:

["https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf"](https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf)

Minimum diameter with counter flection = 100 mm for speed > 2 m/s, This product has not been tested according to ATEX standards (atmospheres with explosion risk - ATEX 95 regulation or EU directive 2014/34/EU) and therefore is subject to user's analysis in the respective environment

Group	Elastomer Covered Conveying Belts
Sub-Group	-
Item number	H010100277

Disclaimer

Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice. EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.