

Endless Round belts

M-RB-K



Main application

Live roller drive belt, Power transmission belt

Description

Elastic, Monolithic Belt, Flexibility in all directions



Product data

Technical data	
Material type	TPU Polyester
Hardness	90 ShA
Temperature correction factor	0.85
Min. operating temperature admissible (continuous)	-20 °C
Max. operating temperature admissible (continuous)	50 °C
Coefficient of friction on steel	0.40

Code	Item number	Color	Food grade	Length	Ø	Package	Quantity	Units	Weight	Weight (i)
				mm	mm				kg	lb
M-RB2.5x078-KG	H950029871	Green	No	78	2.50	Box	1000	EA	0.006	0.0
M-RB2.5x078-KY	H950029873	Yellow	No	78	2.50	Box	1000	EA	0.006	0.0
M-RB2.7x268-KC	H950029876	Cobalt blue	No	268	2.70	Box	1000	EA	0.007	0.0
M-RB2.7x268-KY	H950029879	Yellow	No	268	2.70	Box	1000	EA	0.007	0.0
M-RB2.7x307-KC	H950029880	Cobalt blue	No	307	2.70	Box	1000	EA	0.007	0.0
M-RB2.7x307-KY	H950029882	Yellow	No	307	2.70	Box	1000	EA	0.007	0.0
M-RB3.0x140-KG	H950029883	Green	No	140	3	Box	1000	EA	0.008	0.0
M-RB3.0x175-KG	H950029884	Green	No	175	3	Box	1000	EA	0.008	0.0
M-RB3.0x175-KN	H950029886	Natural	No	175	3	Box	1000	EA	0.008	0.0
M-RB4.0x112-KG	H950029889	Green	No	112	4	Box	1000	EA	0.015	0.0
M-RB4.0x122-KG	H950029890	Green	No	122	4	Box	1000	EA	0.015	0.0
M-RB4.0x258-KC	H950029891	Cobalt blue	No	258	4	Box	1000	EA	0.015	0.0
M-RB5.0x123-KG	H950029892	Green	No	123	5	Box	1000	EA	0.023	0.1
M-RB5.0x182-KG	H950029893	Green	No	182	5	Box	1000	EA	0.023	0.1
M-RB5.0x196-KG	H950029894	Green	No	196	5	Box	1000	EA	0.023	0.1
M-RB6.0x119-KG	H950029895	Green	No	119	6	Box	500	EA	0.033	0.1
M-RB6.0x130-KG	H950029896	Green	No	130	6	Box	500	EA	0.033	0.1
M-RB6.0x142-KG	H950029897	Green	No	142	6	Box	500	EA	0.033	0.1
M-RB6.0x200-KG	H950029898	Green	No	200	6	Box	500	EA	0.033	0.1
M-RB6.5x445-KG	H950029899	Green	No	445	6.50	Box	200	EA	0.039	0.1

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.

Endless Round belts

M-RB-K



Code	Tensile force for 8% elongation (k8% static) (Habasit Standard SOP3-155 / EN ISO 21181):	Tensile force for 8% elongation after relaxation (k8% relaxed) (Habasit Standard SOP3-155 / EN ISO 21181):	Nominal peripheral force	Pulley diameter (minimum)	Minimum pulley diameter running side
	N	N	N	mm	mm
M-RB2.5x078-KG	13	9	16	25	25
M-RB2.5x078-KY	13	9	16	25	25
M-RB2.7x268-KC	15	11	19	27	27
M-RB2.7x268-KY	15	11	19	27	27
M-RB2.7x307-KC	15	11	19	27	27
M-RB2.7x307-KY	15	11	19	27	27
M-RB3.0x140-KG	18	13	23	30	30
M-RB3.0x175-KG	18	13	23	30	30
M-RB3.0x175-KN	18	13	23	30	30
M-RB4.0x112-KG	32	24	41	40	40
M-RB4.0x122-KG	32	24	41	40	40
M-RB4.0x258-KC	32	24	41	40	40
M-RB5.0x123-KG	51	37	65	50	50
M-RB5.0x182-KG	51	37	65	50	50
M-RB5.0x196-KG	51	37	65	50	50
M-RB6.0x119-KG	73	53	93	60	60
M-RB6.0x130-KG	73	53	93	60	60
M-RB6.0x142-KG	73	53	93	60	60
M-RB6.0x200-KG	73	53	93	60	60
M-RB6.5x445-KG	85	62	109	65	65

Chemical resistance

Link to 'Chemical resistance information': <https://rims.habasit.com>

Recommendation

General dimensional tolerance: $\pm 3\%$ or ± 0.20 mm (whichever is greater).

Disclaimer

Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice. EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.