

# Food Belts

## A150COS/LS-B



### Main industry segments


Distribution centers, General conveying, Various industries

### Applications

Packaging belt, Processing belt

### Special features

Oil resistant, Temperature variation resistant



Product Construction / Design	
Conveying side material	Polyvinylchloride (PVC)
Conveying side surface	Smooth
Conveying side property	Adhesive
Conveying side color	Black
Traction layer (material)	Polyester (PET)
Number of Fabrics	1
Pulley side material	Polyester fabric (PET) impregnated with polyvinylchloride (PVC)
Pulley side surface	Impregnated fabric
Pulley side property	Medium-adhesive
Pulley side color	Black

Product characteristics	
Antistatically equipped	No
Adhesive free joining method	Yes
Flammability	No specific flammability prevention property
Food suitability, FDA conformance	No
Food suitability, USDA recommendations	No use intended
Food suitability, EU conformance	No

Technical data			
Thickness of belt	3.8	mm	0.15 inch
Mass of belt (belt weight)	4.8	kg/m <sup>2</sup>	0.980 lb/sqft
Min. operating temperature admissible (continuous)	-23	°C	-10 °F
Max. operating temperature admissible (continuous)	82	°C	180 °F
Coefficient of friction (running side / steel driving pulley)	0.35	-	
Seamless manufacturing width	1524	mm	60 inch
On request other seamless manufacturing width	1829	mm	72 inch

### Joining related properties

Joining method	
Clipper #2HT	Master joining method for standard applications
Flexproof 10 x 80	Optional joining method

[Link to JDS:](#)

Joining method		Clipper #2HT	Flexproof 10 x 80
Pulley diameter (minimum)	mm inch	102 4.00	102 4.00
Pulley diameter minimum with counter flecion	mm inch	102 4.00	102 4.00
Admissible tensile force per unit of width	N/mm lbf/in	26 150	
Admissible tensile force per unit of width at max. operating temperature	N/mm lbf/in	12 69	
Slider bed suitable		Yes	Yes
Carrying rollers suitable		Yes	Yes
Troughed installation suitable		Yes	No
Power turns / curved installations		No	No
Nosebar suitable		No	No
Metal detector suitable		Yes	No

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554).

### Chemical resistance

Link to 'Chemical resistance information': <http://www.habasit.com/en/chemical-resistance.htm>

### Mode of use or conveyance

Declined, Horizontal, Inclined

### Calculations

For most applications calculation is not required. Should you still need a calculation: please ask Habasit.

### Recommendation

Do not go below initial elongation (epsilon) ~ 0.5%, Install the slack belt and tension until running perfectly under the full belt load

For details consult 'Storage and handling requirements for belts and machine tapes' or contact Habasit, Protect belts from sunlight/UV-radiation/dust and dirt. Store spare belts in a cool and dry place and if possible in their original packaging.

No danger and limitation

Group	Woven PVC Belts
Sub-Group	Allveyor General Purpose Belts
Item number	H2500001431

### Disclaimer

#### Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice.  
EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.