

# Food Belts A200COS-W



Only for Habasit Nippon

## Main industry segments



Fruit, Vegetables

## Applications

Food processing/conveying belt, Packaging belt

## Special features

Oil resistant, Temperature variation resistant



Product Construction / Design	
Conveying side material	Polyvinylchloride (PVC)
Conveying side surface	Smooth
Conveying side property	Adhesive
Conveying side color	White
Traction layer (material)	Polyester (PET)
Number of Fabrics	1
Pulley side material	Polyester fabric (PET) impregnated with polyvinylchloride (PVC)
Pulley side surface	Impregnated fabric
Pulley side property	Non-adhesive
Pulley side color	White

Product characteristics	
Antistatically equipped	No
Adhesive free joining method	Yes
Flammability	No specific flammability prevention property
Food suitability, FDA conformance	Yes - Check Document of Compliance (DoC) in our Portal
Food suitability, USDA recommendations	No use intended
Food suitability, EU conformance	No
Other conformance/approval	Japanese Food Regulation (MHLW Notification No. 370)

FDA, 21 CFR parts/sections 175.300 Resinous and polymeric coatings, 177.1630 Polyethylene phthalate polymers, 178.3297 Colorants for polymers This product meets the relevant requirements laid down in this regulation and is applicable for direct contact with: - dry food (dry solids with the surface containing no free fat or oil, no end test required) as listed in 21 CFR 176.170 (c) table 1, food type VIII Conditions of use D (hot filled or pasteurized below 150 degF) through G (frozen) as listed in 21 CFR 175.300(d) table 2

Technical data			
Thickness of belt	5.2	mm	0.21 inch
Mass of belt (belt weight)	6.3	kg/m <sup>2</sup>	1.300 lb/sqft
Tensile force for 1% elongation (k1% static) per unit of width (Habasit standard SOP3-155)	20	N/mm	114 lbf/in
Tensile force for 1% elongation after relaxation (k1% relaxed) per unit of width (Habasit Standard SOP3-155 / EN ISO 21181)	15	N/mm	86 lbf/in
Min. operating temperature admissible (continuous)	-23	°C	-10 °F
Max. operating temperature admissible (continuous)	82	°C	180 °F
Coefficient of friction (pulley side / steel driving pulley)	0.30	-	
Coefficient of friction (pulley side / driving pulley with friction cover)	0.40	-	
Coefficient of friction (pulley side / pickled steel slider bed)	0.35	-	
Coefficient of friction (pulley side / phenolic resin slider bed)	0.35	-	
Coefficient of friction (pulley side / stainless steel slider bed)	0.30	-	
Seamless manufacturing width	1524	mm	60.00 inch
On request other seamless manufacturing width	1829	mm	72 inch

## Joining related properties

Joining method	
Clipper #3	Master joining method for standard applications
Flexproof 10 x 80	Optional joining method

[Link to JDS:](#)

Joining method		Clipper #3	Flexproof 10 x 80
Pulley diameter (minimum)	mm inch	152 6.00	152 6.00
Pulley diameter minimum with counter flecion	mm inch	165 6.50	165 6.50
Admissible tensile force per unit of width	N/mm lbf/in	32 183	
Slider bed suitable		Yes	Yes
Carrying rollers suitable		Yes	Yes
Troughed installation suitable		No	
Powerturns / curved installations		No	No
Knife-edge (nosebar) suitable		No	No
Metal detector suitable		No	No

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.

# Food Belts A200COS-W



## Chemical resistance

Link to 'Chemical resistance information': <https://rims.habasit.com>

## Mode of use or conveyance

Declined, Horizontal, Inclined

## Calculations

For most applications calculation is not required. Should you still need a calculation: please ask Habasit.

## Recommendation

Do not go below initial elongation (epsilon) ~ 0.5%, Install the slack belt and tension until running perfectly under the full belt load

Store spare belts in a cool and dry place and if possible in their original packaging. Protect spare belts from sunlight/UV-radiation/dust/dirt! Check Link for Storage requirements:

["https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf"](https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf)

No danger and limitation

Group	PVC Belts
Sub-Group	Oil Resistant Belts
Item number	H250000701

## Disclaimer

### Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice. EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.